



\*\* ERTACETAL® is the registered trademark of

## QUADRANT

### PRODUCT CAPABILITIES:

- Rod : Dia. 3mm - 320mm
- Heavy Gauge Sheet : 0.5mm - 120mm
- Tube : OD. 20mm - 350mm

### ADVANTAGES:

- High Mechanical Strength, Stiffness And Hardness
- Excellent Resilience
- Good Creep Resistance
- High Impact Strength, Even At Low Temperatures
- Very Good Dimensional Stability (Low Water Absorption)
- Good Sliding Properties And Wear Resistance
- Excellent Machinability

### PRODUCT COLORS:

- White (Natural)
- Black

### APPLICATIONS INCLUDE:

- Gear Wheels With Small Modulus
- Cams
- Heavily Loaded Bearings And Rollers
- Valve Seats
- Bearings And Gears With Small Clearances

GENERAL PROPERTIES	Test Method ISO ( IEC )	ERTACETAL® H Typical Values
<b>PHYSICAL</b>		
Specific Gravity (g/cm <sup>3</sup> )	1183	1.43
Water Absorption, 24 hrs (%)	62	0.21
<b>MECHANICAL</b>		
Tensile Stress at Yield (MPa)	527	78
Tensile Strain at Break (%)	527	35
Tensile Modulus of Elasticity (MPa)	527	3,600
Charpy Impact Strength, Un-Notched (kJ/m <sup>2</sup> )	179/1eU	≥200
Charpy Impact Strength, Notched (kJ/m <sup>2</sup> )	179/1eA	10
IZOD Impact Strength, Notched (kJ/m <sup>2</sup> )	180/2A	10
Rockwell Hardness	2039-2	M 88
<b>THERMAL</b>		
Coeff. of Linear Thermal Expansion ( m/[m.k] )	-	95 x 10 <sup>-6</sup>
Heat Deflection Temp (°F / °C) @ 1.8 MPa	75	239 / 115
Thermal Conductivity at 23 °C ( W/[m.k] )	-	0.31
Melting Temperature (°F / °C)	-	347 / 175
Flammability Rating @ ( 3 mm thickness )	UL-94	HB
<b>ELECTRICAL</b>		
Surface Resistivity (ohms/sq)	{60093}	> 10 <sup>13</sup>
Volume Resistivity (ohm-cm)	{60093}	> 10 <sup>14</sup>
Dielectric Dissipation Factor Tan δ : at 100 Hz	{60250}	0.003

NOTE: The information contained here in is typical values intended for reference only. They should NOT be used as a basis for design specifications or quality control.