



\*\* NYLATRON® is the registered trademark of

## QUADRANT

Nylon offer extremely good wear resistance, couple with high tensile strength and modulus of elasticity. They also have high impact resistance, a high heat distortion temperature, and resist wear, abrasion, and vibration. In addition, nylons can withstand sustained contact with a wide variety of chemicals, alkalies, dilute acids or oxidizing agents.

### ADVANTAGES:

- High Mechanical Strength, Stiffness, Hardness And Toughness · Good Fatigue Resistance
- High Mechanical Damping Ability · Good Sliding Properties · Excellent Wear Resistance
- Good Electrical Insulating Properties · High Resistance Against High Energy Radiation (Gamma And X-rays) · Good Machinability

### APPLICATIONS INCLUDE:

- Sleeve And Slide Bearings · Cutting And Chopping Boards · Support And Guide Wheels
- Sleeves For Wheels And Rollers, Pulleys And Pulley-Linings, Cams · Conveyor Rollers · Tension Rollers · Buffer Blocks · Hammer Heads · Scrapers · Gear Wheels · Starwheels · Sprockets · Feed Screws · Seal-Rings · Wear Pads · Insulators

GENERAL PROPERTIES	Test Methods ISO / (IEC)	NYLATRON MC 901 (Cast)	NYLATRON GSM (Cast)	NYLATRON NSM (Cast)	NYLATRON GS (Extruded)
<b>COLOUR</b>		● Blue	● Grey-Black	● Grey	● Grey-Black
<b>PHYSICAL</b>					
Specific Gravity (g/cm <sup>3</sup> )	1183	1.15	1.16	1.14	1.15
Water Absorption, 24 hrs (%)	62	0.72	0.76	0.59	0.68
<b>MECHANICAL @ 73°F</b>					
Tensile Stress at Yield (MPa)	527	81	78	76	92
Tensile Strain at Break (%)	527	35	25	25	20
Tensile Modulus of Elasticity (MPa)	527	3,200	3,300	3,100	3,500
Charpy Impact Strength, Un-Notched (kJ/m <sup>2</sup> )	179/1eU	No Break	No Break	≥ 100	No Break
Charpy Impact Strength, Notched (kJ/m <sup>2</sup> )	179/1eA	3.5	3.5	4	4
IZOD Impact Strength, Notched (kJ/m <sup>2</sup> )	180/2A	3.5	3.5	4	4
Rockwell Hardness	2039-2	M 85	M 84	M 81	M 88
<b>THERMAL</b>					
Coeff. of Linear Thermal Expansion ( m/[m.k] )	-	80 x 10 <sup>-6</sup>	80 x 10 <sup>-6</sup>	80 x 10 <sup>-6</sup>	80 x 10 <sup>-6</sup>
Heat Deflection Temp (°F / °C) @ 1.8 MPa	75	176 / 80	176 / 80	167 / 75	185 / 85
Thermal Conductivity at 23 °C ( W/[m.k] )	-	0.29	0.3	0.29	0.29
Flammability Rating @ ( 3mm thickness )	UL-94	HB	HB	HB	HB
<b>ELECTRICAL</b>					
Surface Resistivity (ohms/sq)	{60093}	> 10 <sup>13</sup>	> 10 <sup>13</sup>	> 10 <sup>13</sup>	> 10 <sup>13</sup>
Volume Resistivity (ohm-cm)	{60093}	> 10 <sup>14</sup>	> 10 <sup>14</sup>	> 10 <sup>14</sup>	> 10 <sup>14</sup>
Dielectric Dissipation Factor Tan δ : at 100 Hz	{60250}	0.012	0.012	0.012	0.013

NOTE: The information contained here in is typical values intended for reference only. They should NOT be used as a basis for design specifications or quality control.