



PROPYLUX® SD-X7

Static Dissipative Polypropylene / Static Dissipative PP



** PROPYLUX® is the registered trademark of

WESTLAKE PLASTICS COMPANY

PRODUCT CAPABILITIES:

- Heavy Gauge Sheet :1/4" - 2"

ADVANTAGES:

- Low Carbon Concentrations 1% To 2%
- Permanently Static Dissipative
- Non-Sloughing
- Low Leachable Ion Levels
- Low Outgassing

PRODUCT COLORS:

- Black

APPLICATIONS INCLUDE:

- Transfer Pallets
- Equipment In The Electrical/Electronic Or Semiconductor Industry

GENERAL PROPERTIES	ASTM or UL Test	PROPYLUX® SD-X7 Typical Values
PHYSICAL		
Specific Gravity (g/cm ³)	D792	1.01
Water Absorption, 24 hrs (%)	D570	0.03
MECHANICAL		
Tensile Strength (psi)	D638	6,500
Tensile Elongation at Yield (%)	D638	2
Flexural Strength (psi)	D790	-
Flexural Modulus (psi)	D790	450,000
IZOD Notched Impact (ft-lb/in)	D256	0.94
IZOD Un-Notched Impact (ft-lb/in)	D256	6.8
Hardness, Shore D	D2240	-
THERMAL		
Coeff. of Thermal Expansion (x 10 ⁻⁵ in./in./°F)	D696	-
Heat Deflection Temp (°F / °C) @ 264 psi	D648	300 / 149
Thermal Conductivity (BTU-in/ft ² -hr-°F)	C177	-
Flammability Rating @ .030"	UL-94	-
ELECTRICAL		
Surface Resistivity (ohms/sq)	D257	10 ⁶ - 10 ⁹
Volume Resistivity (ohm-cm) at 73°F, 50% RH	D257	10 ⁶ - 10 ⁹
Static Decay, 15% RH (seconds)	MIL-B-81705-B	-

NOTE: The information contained here in is typical values intended for reference only. They should NOT be used as a basis for design specifications or quality control.