



# SEMITRON® ESD 500HR

Static Dissipative Reinforced PolyTetraFluoroEthylene / Static Dissipative PTFE



### PRODUCT CAPABILITIES:

- Sheet : 3/8" - 2"

### PRODUCT COLORS:

- White

### ADVANTAGES:

- Thermally Stable To Temperatures of 500°F (260°C) Without Degradation
- High Thermal Insulation
- Low Coefficient of Friction

### APPLICATIONS INCLUDE:

- Integrated Circuits
- Hard Disk Drives
- Wafer Combs
- Boat Inserts
- Wear Guides
- Vacuum Wand Tips
- Thermal Isolators
- Handling Trays
- Retaining Rings
- Vacuum Wand

\*\* SEMITRON® is the registered trademark of

## QUADRANT

GENERAL PROPERTIES	ASTM or UL Test	SEMITRON® ESD500HR Typical Values
<b>PHYSICAL</b>		
Specific Gravity (g/cm <sup>3</sup> )	D792	2.3
Water Absorption, 24 hrs (%)	D570	0.03
<b>MECHANICAL</b>		
Tensile Strength (psi)	D638	1,100
Tensile Modulus (psi)	D638	300,000
Tensile Elongation at Break (%)	D638	10
Flexural Strength (psi)	D790	2,200
Flexural Modulus (psi)	D790	500,000
Compressive Strength (psi)	D695	4,000
Compressive Modulus (psi)	D695	250,000
Hardness, Rockwell	D785	R50
IZOD Notched Impact (ft-lb/in)	D256	1
<b>THERMAL</b>		
Coeff. of Thermal Expansion (x 10 <sup>-5</sup> in./in./°F)	E831	5.7
Heat Deflection Temp (°F / °C) @ 264 psi	D648	270 / 132
Melting Temp (°F / °C)	D3418	621 / 327
Max Operating Temp (°F / °C)	-	500 / 260
Thermal Conductivity (BTU-in/ft <sup>2</sup> -hr-°F)	F433	5.3
Flammability Rating	UL-94	V-O
<b>ELECTRICAL</b>		
Surface Resistivity (ohms/sq)	EOS/ESD S11.11	10 <sup>10</sup> - 10 <sup>12</sup>
Volume Resistivity (ohm-cm) at 50% RH	D257	10 <sup>10</sup> - 10 <sup>12</sup>
Dielectric Constant at 1KHz	D150	2.9

NOTE: The information contained here in is typical values intended for reference only. They should NOT be used as a basis for design specifications or quality control.